

Human mesenchymal stromal cell adhesion and expansion on fluoropolymer surfaces modified with oxygen and nitrogen-rich plasma polymers

Balaji Ramachandran^{1†}, Gad Sabbatier^{1†}, Olivia Bowden¹, Katie Campbell², Natalie Fekete²,

Pierre-Luc Girard-Lauriault¹, Corinne A. Hoesli^{1}*

¹Department of Chemical Engineering, McGill University, Montréal, Canada

²Saint-Gobain Ceramics & Plastics, Inc., Northboro R&D Center, Northborough, Massachusetts

*Correspondence: Corinne Hoesli, Department of Chemical Engineering, McGill University, Montréal, QC, Canada H3A 0C5. Email id: corinne.hoesli@mcgill.ca Tel no: 5143984275

†These authors contributed equally to this work.

This article has been accepted and published in the Journal “Colloids and Surfaces B: Biointerfaces” DOI: <https://doi.org/10.1016/j.colsurfb.2023.113740>

1. Supporting Information

Table S1.1. Root mean square roughness of unmodified, modified, and sterilized FEP films

Sample	Roughness Rq (nm)	
	Before sterilization	After sterilization
FEP	7.9 ± 0.5	12 ± 1
O-rich PPCs	31 ± 8	27 ± 4
N-rich PPCs	10 ± 2	51 ± 10

Table S1.2. Percentage of positive cells cultured on different surfaces

Surface Marker expression	Control	FEP (untreated)	O-rich PPCs	N-rich PPCs	TCPS (Nunclon™ Delta)
CD105	99.09 ± 0.71	95.33 ± 3.97	98.65 ± 1.35	96.12 ± 2.33	97.50 ± 1.25
CD73	99.85 ± 0.13	95.53 ± 3.09	94.84 ± 2.53	97.02 ± 2.98	98.93 ± 0.97
CD90	100.0 ± 0.00	100.0 ± 0.00	99.97 ± 0.03	96.90 ± 2.76	100.0 ± 0.0
CD45	0	0	0.11 ± 0.06	0	0
CD34	1.430 ± 2.44	0	0.20 ± 0.20	13.47 ± 6.42	1.40 ± 1.25
CD14	0.040 ± 0.05	4.77 ± 4.77	0	0.27 ± 0.27	0.26 ± 0.26
CD19	0	3.10 ± 1.84	0	0	0
HLA-DR	0.010 ± 0.01	0	0.07 ± 0.07	1.74 ± 1.74	0