

## Supplementary Material for the Paper:

### “Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*

Reza Fayaz<sup>1,5,6</sup>, Antoine Carissimo<sup>3,5,6</sup>, Md Izzuddin Jundullah Hanafi<sup>4,5</sup>, Guillaume Pillot<sup>3,5,6</sup>, Michael Baune<sup>1,6</sup>, Thorsten M. Gesing<sup>4,5</sup>, Sven Kerzenmacher<sup>3,5,6</sup>, Fabio La Mantia<sup>2,5,6</sup> & Jorg Thöming<sup>1,5,6\*</sup>

<sup>1</sup>University of Bremen, Chemical Process Engineering Group (CVT), Leobener Strasse 6, 28359 Bremen, Germany

<sup>2</sup>University of Bremen, Energy Storage and Conversion Systems, Wiener Strasse 12, 28359 Bremen, Germany

<sup>3</sup>University of Bremen, Environmental Process Engineering Group (UVT), Leobener Strasse 6, 28359 Bremen, Germany

<sup>4</sup>University of Bremen, Institute of Inorganic Chemistry and Crystallography, Leobener Strasse 7, 28359 Bremen, Germany

<sup>5</sup>University of Bremen, MAPEX Center for Materials and Processes, Bibliothekstrasse 1, 28359 Bremen, Germany

<sup>6</sup>University of Bremen, Center for Environmental Research and Sustainable Technology (UFT), Leobener Strasse 6, 28359 Bremen, Germany


## List of Figures:

- Fig. S-1:** The iron-reducing bacterium *C. ferrireducens* used the iron oxide/hydroxide as a terminal electron acceptor for anaerobic respiration. (a) A full magnetic response was observed after two days of cultivation. (b) Black magnetic particles from *C. ferrireducens* cultures were observed with transmitted white light (see Fig. 1b for the fluorescent image). .. 2
- Fig. S-2:** X-ray powder data Rietveld (XRPD) plots of iron oxide/hydroxide as the starting material, the biologically produced magnetite (bio-magnetite), and that after calcining (bio-hematite). XRPD data confirms that bio-mining has successfully converted a quantum-crystalline ferrihydrite with an average crystallite size (ACS) of 2.7(1) nm into a micro-crystalline bio-magnetite (ACS = 16.2(2) nm). Heat treatment increased the ACS further to 238(6) nm for bio-hematite. .... 3
- Fig. S-3:** The PDF EnvACS method to determine the ACS of iron oxide/hydroxide. .... 4
- Fig. S-4:** The first cycle of cyclic voltammetry test in 10 M NaOH for iron oxide/hydroxide as starting material, the biologically produced magnetite (bio-magnetite), and after heat treatment (bio-hematite) at 363 K and the obtained iron yields. No redox peaks appear as the materials are not yet electrochemically activated. .... 5
- Fig. S-5:** Visualization of the inverse relationship between specific surface area (logarithmic scale) and current efficiencies for iron oxide/hydroxide as starting material, the biologically produced magnetite, and after heat treatment (bio-hematite) after conducting 20 h chronoamperometry at -1.4 V vs. Ag/AgCl in 10 M NaOH at 363 K. The numbers in brackets are the estimated standard deviations of the obtained values in the last digit. .... 6
- Fig. S-6:** Elemental map data of a reduced bio-hematite after 20 h of electrolysis at -1.4 V vs. Ag/AgCl in 10 M NaOH at 363 K shows areas where Fe is inclusively present. Note that silver appears as a binder during pelletizing and that the presence of oxygen stains from the ambient atmosphere in the SEM chamber is unavoidable. .... 7
- Fig. S-7:** EDX analysis reveals traces of carbon in the bio-magnetite, probably from dead microorganisms or the partial formation of siderite (FeCO<sub>3</sub>). .... 8

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*




**Fig. S-1:** The iron-reducing bacterium *C. ferrireducens* used the iron oxide/hydroxide as a terminal electron acceptor for anaerobic respiration. (a) A full magnetic response was observed after two days of cultivation. (b) Black magnetic particles from *C. ferrireducens* cultures were observed with transmitted white light (see Fig. 1b for the fluorescent image).

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*



**Fig. S-2:** X-ray powder data Rietveld (XRPD) plots of iron oxide/hydroxide as the starting material, the biologically produced magnetite (bio-magnetite), and that after calcining (bio-hematite). XRPD data confirms that bio-mining has successfully converted a quantum-crystalline ferrihydrite with an average crystallite size (ACS) of 2.7(1) nm into a micro-crystalline bio-magnetite (ACS = 16.2(2) nm). Heat treatment increased the ACS further to 238(6) nm for bio-hematite.

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*





Fig. S-3: The PDF EnvACS method to determine the ACS of iron oxide/hydroxide.

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*




**Fig. S-4:** The first cycle of cyclic voltammetry test in 10 M NaOH for iron oxide/hydroxide as starting material, the biologically produced magnetite (bio-magnetite), and after heat treatment (bio-hematite) at 363 K and the obtained iron yields. No redox peaks appear as the materials are not yet electrochemically activated.

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*




**Fig. S-5:** Visualization of the inverse relationship between specific surface area (logarithmic scale) and current efficiencies for iron oxide/hydroxide as starting material, the biologically produced magnetite, and after heat treatment (bio-hematite) after conducting 20 h chronoamperometry at -1.4 V vs. Ag/AgCl in 10 M NaOH at 363 K. The numbers in brackets are the estimated standard deviations of the obtained values in the last digit.

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*




**Fig. S-6:** Elemental map data of a reduced bio-hematite after 20 h of electrolysis at -1.4 V vs. Ag/AgCl in 10 M NaOH at 363 K shows areas where Fe is inclusively present. Note that silver appears as a binder during pelletizing and that the presence of oxygen stains from the ambient atmosphere in the SEM chamber is unavoidable.

Supplementary Material for the Paper:

“Electrochemical Iron Recovery from Biologically Produced Magnetite via Iron Oxide/Hydroxide Conversion: First Steps towards Terrestrial and Martian Applications”

*Journal of Sustainable Metallurgy*



**Fig. S-7:** EDX analysis reveals traces of carbon in the bio-magnetite, probably from dead microorganisms or the partial formation of siderite ( $\text{FeCO}_3$ ).