Computational optimized finite element modelling of mechanical interaction of concrete with fiber reinforced polymer

Khosro Shahpoori Arani¹, Yousef Zandi², Binh Thai Pham^{*3}, M.A. Mu'azu⁴, Javad Katebi⁵, Mohammad Mohammadhassani⁶, Seyedamirhesam Khalafi⁷, Edy Tonnizam Mohamad⁸, Karzan Wakil⁹ and Majid Khorami¹⁰

¹Department of Civil Engineering, Qeshm International Branch, Islamic Azad University, Qeshm, Iran

²Department of Civil Engineering, Tabriz Branch, Islamic Azad University, Tabriz, Iran

³Institute of Research and Development, Duy Tan University, Da Nang 550000, Vietnam

⁴Department of Civil Engineering, Jubail University College, Royal Commission of Jubail and Yanbu, Jubail, Saudi Arabia ⁵Faculty of Civil Engineering, University of Tabriz, Tabriz, Iran

⁶Seismology Engineering & Risk Department, Road, Housing & Urban Development Research Center (BHRC), Tehran, Iran

⁷Department of Construction Management, University of Houston, USA

⁸Centre of Tropical Geoengineering (GEOTROPIK), Faculty of Civil Engineering, Universiti Teknologi Malaysia, Johor Bahru, Malaysia ⁹Research Center, Sulaimani Polytechnic University, Sulaimani 46001, Kurdistan Region, Iraq

¹⁰Facultad de Arquitectura y Urbanismo, Universidad Tecnológica Equinoccial, Calle Rumipamba s/n y Bourgeois, Quito, Ecuador

(Received June 18, 2018, Revised January 12, 2019, Accepted January 22, 2019)

Abstract. This paper presents a computational rational model to predict the ultimate and optimized load capacity of reinforced concrete (RC) beams strengthened by a combination of longitudinal and transverse fiber reinforced polymer (FRP) composite plates/sheets (flexure and shear strengthening system). Several experimental and analytical studies on the confinement effect and failure mechanisms of fiber reinforced polymer (FRP) wrapped columns have been conducted over recent years. Although typical axial members are large-scale square/ rectangular reinforced concrete (RC) columns in practice, the majority of such studies have concentrated on the behavior of small-scale circular concrete specimens. A high performance concrete, known as polymer concrete, made up of natural aggregates and an orthophthalic polyester binder, reinforced with non-metallic bars (glass reinforced polymer) has been studied. The material is described at micro and macro level, presenting the key physical and mechanical properties using different experimental techniques. Furthermore, a full description of non-metallic bars is presented to evaluate its structural expectancies, embedded in the polymer concrete matrix. In this paper, the mechanism of mechanical interaction of smooth and lugged FRP rods with concrete is presented. A general modeling and application of various elements are demonstrated. The contact parameters are defined and the procedures of calculation and evaluation of contact parameters are introduced. The method of calibration of the calculated parameters is presented. Finally, the numerical results are obtained for different bond parameters which show a good agreement with experimental results reported in literature.

Keywords: fiber-reinforced polymers; reinforced concrete (FRP); mechanical interaction; bond; contact; friction

1. Introduction

Many researches has been conducted recently on behavior of reinforced concrete in the application of many structure members like concrete beam without FRP (Mohammadhassani *et al.* 2013, Mohammadhassani *et al.* 2014a, Mohammadhassani *et al.* 2014b, Mohammadhassani *et al.* 2014c, Khorramian *et al.* 2015, Khorramian *et al.* 2016, Khorami *et al.* 2017b, Khorramian *et al.* 2017, Mansouri *et al.* 2017, Nasrollahi *et al.* 2018, Nosrati *et al.* 2018, Paknahad *et al.* 2018, Sadeghipour Chahnasir *et al.* 2018) and with FRP strengthening (Rahimi and Hutchinson 2001, Karimi *et al.* 2011, Sinaei *et al.* 2011, Ashour and Kara 2014, Moy 2018). From the recent researches on application of reinforced concrete in steel and composite beams, the non-strengthening beams' ultimate loads have

E-mail: phambinhgtvt@gmail.com

been investigated (Kheyroddin 2008a, Shariati et al. 2010, Shariati et al. 2011a, Shariati et al. 2011b, Shariati et al. 2011c, Sinaei et al. 2011, Shariati et al. 2012a, Shariati et al. 2012b, Shariati et al. 2012c, Shariati et al. 2012d, Shariati et al. 2012e, Sinaei et al. 2012, Mohammadhassani al. 2013, Shariati 2013, Shariati et al. 2013, et Mohammadhassani et al. 2014a, Mohammadhassani et al. 2014b, Mohammadhassani et al. 2014c, Shariati 2014, Shariati et al. 2014a, Shariati et al. 2014b, Toghroli Ali et al. 2014, Khorramian et al. 2015, Shariati et al. 2015, Khorramian et al. 2016, Safa et al. 2016, Shahabi et al. 2016a, Shahabi et al. 2016b, Shariati et al. 2016, Tahmasbi et al. 2016, Toghroli et al. 2016, Khorramian et al. 2017, Mansouri et al. 2017, Shariati et al. 2017, Bazzaz 2018, Bazzaz et al. 2018, Hosseinpour et al. 2018, Nasrollahi et al. 2018, Paknahad et al. 2018, Sadeghipour Chahnasir et al. 2018, Sedghi et al. 2018, Shariat et al. 2018, Shariati et al. 2018, Wei et al. 2018). The FRP reinforcement rods have been introduced as replacement for steel rods in environments, which are, capable of chemical and

^{*}Corresponding author, Ph.D.

electromagnetically corrosion (Sinaei *et al.* 2011). The acceptance of FRP reinforcing bars in structural engineering has been inhibited partly due to lack of design criteria, particularly with regard to bond (Feroldi and Russo 2016). Several techniques have been developed to inhibit or eliminate corrosion, including epoxy-coated reinforcing bars, synthetic membranes, latex concrete, Cathodic protection, special paints, and Sealants (Benmokrane and Tighiouart 1996).

The FRP material is transversely anisotropic. As a result, their mechanical properties in longitudinal direction differ from the other two orthogonal directions. Many experimental studies have demonstrated that the key properties of the physical and mechanical behavior of FRP rebars are qualitively and quantitively different from the well-known properties of steel rebars (Cosenza *et al.* 1997). In recent years many experimental studies have been conducted in order to investigate bond between FRP rebars and concrete. However, fewer researches have been carried out by scientists on modelling and simulation of bond of FRP rebars to concrete. The aim of this paper is to propose a reliable FE modelling of mechanical interaction of smooth rods with the surrounding concrete by evaluation, calibration and validation of contact parameters.

Retrofit of reinforced concrete (RC) members using externally bonded fibre reinforced polymer (FRP) components has become a very common practice, widely recognized by modern design codes (Naderpour et al. 2011, Sinaei et al. 2011, Ashour and Kara 2014, Mohebi et al. 2016, Naderpour et al. 2016). In particular, the flexural strength of a beam can be significantly increased by application of carbon (CFRP) or glass (GFRP) FRP plates/sheets adhesively bonded to the beam tension face. This paper focuses on efficient and accurate finite element (FE) modelling of RC beams flexurally retrofitted with externally bonded FRP plates/sheets. The finite element modeling has been followed those of previously conducted researches (Kheyroddin 2008b, Arabnejad Khanouki et al. 2010, Arabnejad Khanouki et al. 2011, Daie et al. 2011, Jalali et al. 2012, Aghakhani et al. 2015, Bazzaz et al. 2015, Khanouki et al. 2016, Mansouri et al. 2016, Safa et al. 2016, Toghroli et al. 2016, Khorami et al. 2017a, Mansouri et al. 2017, Bazzaz 2018, Heydari and Shariati 2018, Hosseinpour et al. 2018, Ismail et al. 2018, Mehrmashhadi et al. 2018a, Mehrmashhadi et al. 2018b, Sedghi et al. 2018, Toghroli et al. 2018a, Toghroli et al. 2018b, Zhao et al. 2018).

FRP-retrofit of RC beams for flexural strengthening presents numerous advantages compared to other flexural strengthening techniques, e.g., strengthening using steel plates. Some of these advantages are: small increase in structural size and weight, easy transportation, speed and simplicity of in-situ application, and good resistance to corrosion and other degradation processes due to hostile environmental conditions. This technique has found numerous applications in retrofitting of bridges and buildings during the last two decades. At the same time, extensive experimental, analytical and numerical research has been carried out to understand and model the structural behavior of FRP-strengthened RC beams. For literature

reviews on different aspects of FRP-strengthening of RC structures, the interested reader is referred to (Jalal et al. 2013, Nazerian and Sadeghiipanah 2013, Ashour and Kara 2014, Mohebi et al. 2016). Particular attention has been given to recognizing and understanding the failure modes that RC beams retrofitted with FRP can experience. The experimentally identified failure modes can be grouped as follows: (1) flexural failure by concrete crushing or by steel yielding followed by concrete crushing (flexure failure mode, which is similar to the failure mode of conventional/non-retrofitted RC beams), (2) flexural failure due to FRP rupture (FRP rupture failure mode), (3) flexural failure due to plate end interfacial debonding to concrete cover separation or to intermediate crack induced debonding (debonding failure mode), and (4) shear failure. A more detailed description of these failure modes can be found in (Rahimi and Hutchinson 2001, Naderpour et al. 2016). It is noteworthy that all the failure modes typical of FRP-retrofitted beams (i.e., FRP rupture and debonding) are brittle in nature. In addition, the debonding failure modes correspond to a less than optimal use of the strength capabilities of the FRP material. In order to increase the efficiency of the FRP-retrofit reducing the impact of debonding failure modes, mechanical anchorage techniques have been devised and employed, e.g., use of mechanical devices at the FRP plate/sheet ends, FRP sheets wrapped around the RC member at the FRP plate/sheet ends (Uwrap), and U-shaped FRP plates/sheets along the entire length of the RC beam (U-shape) (Hadi 2007).

In the existing literature, numerous studies deal with modelling of FRP-strengthened RC members for bending behaviour and correlation of experimental results with numerically predicted ultimate flexural strength, e.g., (Hadi 2007). Understanding and modelling of debonding failure modes has been and still is a very active field of research, mainly due to the complexity of the problem at hand. Indeed, there is a strong need of reliable and robust formulations of specialized FEs that could help researchers to model accurately FRP strengthened RC members and structures in order to predict their response under different strengthening configurations, e.g., for design-oriented parametric studies.

Previous FE studies of FRP-retrofitted beams involve the use of refined FE meshes of (1) frame elements with an increased number of DOFs per element when compared to a classical Euler-Bernoulli frame element (Triantafillou and Plevris 1992), (2) two-dimensional plate/shell elements (Jerome and Ross 1997), or (3) three-dimensional solid elements (Yang et al. 2009). The high computational cost of structural response analyses based on FE models such as the ones referred above has prompted the development of purely numerical methods (i.e., not based on mechanics) for the analysis and design of FRP-strengthened RC structures (Yang et al. 2009). The research work presented in this paper develops a new nonlinear frame FE, based on the classical Euler-Bernoulli assumptions, and able to model the mechanical behaviour of FRP-strengthened RC beams. This FE, referred to as FRP-FB-beam in the sequel, (1) allows reducing the complexity and computational cost of FE analyses based on existing FE models, (2) provides a



Fig. 1 The tangential and normal behavior of contact element

sound mechanical description and interpretation of the phenomena leading to failure of FRP-retrofitted RC beams, and (3) simulates the structural response of the considered structural systems with accuracy satisfactory for practical applications.

2. Mechanical interaction of FRP smooth and lugged rods with concrete

Bond strength is more affected by the low transverse stiffness which is dependent mostly on the matrix material. The bond mechanism of FRP reinforcement with concrete consists of two different aspects; the major and minor phenomena. The major phenomena are: friction and mechanical interferences, including bearing between lugs and the blocks of concrete. The former is the main cause of mechanical interaction in smooth rods while the latter mainly happens in the lugged rods. The minor phenomena are chemical adhesion, temperature and moisture effects and cog wheel behavior between the rib and core of reinforcement after shear cut-off takes place. The commonly used bond strength calculated by the division of the pull out force by the area of embedment length decreases as the embedment length increases for a specified db which is the diameter of bar (Cosenza et al. 1997).

The tolerance mechanism of pull-out load in the lugged rods is mainly based on bearing between the ribs and blocks of concrete. In fact, it is the reason of occurrence of general failure in system, such as "concrete splitting" or "rib cutoff". If concrete splitting happens in all concrete blocks below the ribs the main factor to provide further bond strength is the friction between different parts of concrete on both sides of the gap. However, in the case of lug shear cut-off the main factor, which provides bond strength, is the so-called "cog wheel" behavior between the cut lugs and the internal core of reinforcement.

It must be noted that decreasing the deformation depth results in some decrease in bond strength. The analytical results show that in the case of large bond lengths (larger than about 15 times the diameter), the analytical bond splitting strength is inversely proportional to the bond length and is clearly influenced by the Young modulus (Sakai *et al.* 1999). Bakis developed a simplified model of the mechanical interaction without explicitly modelling the geometry of the surface structure (Guo and Cox 2000).

3. Numerical modelling

In order to simulate the mechanical interaction of smooth rods with concrete, the contact elements are employed in the contact area between the reinforcement and concrete cylinder. The contact element involves two stiffness components: The tangential (frictional) and normal components. Another parameter, which is basically applied in the definition of contact, is the coefficient of friction μ . A tension cut-off model is used in the normal direction of interface element, while in compression it behaves linear with stiffness coefficient Kn through the whole linear zone, as shown in Fig. 1. An elasto-plastic frictional behavior is considered for the tangential behavior of interface, in which the maximum tolerable tangential force; Fs, is μ Fn. When the concrete is casted in the prepared framework, it behaves as a fluid for a while without any capability to exert a pressure on the reinforcement inside. It gradually becomes more stiff and solid. Cement hydration produces a temperature gradient through the whole concrete and results in different temperature of the reinforcement and concrete. Considering different coefficient of temperature expansion the two materials possess, some initial pressure is exerted through the boundary of adjacent materials which is defined by some initial interference of contact element and is equal to radial stiffness *Kn* times the initial interference.

In order to model the chemical adhesion between the concrete and rod, which is one of the suppliers of bond especially at initial stages of loading, some nonlinear springs have been used. The proposed equation for forcedisplacement curve of nonlinear springs by Al-Zahrani is Ae-Bd, where A and B are variable parameters (Bakis *et al.* 1998). It means that by increasing the amount of relative displacement, the total tolerable force of nonlinear springs, which indicates the adhesion force, decreases exponentially. In the above formula, d is the relative displacement.

The model used in this analysis is axisymmetric so only one half of the experimental specimen is modeled. Fig. 2 illustrates a part of the model applied for simulation of smooth FRP rod pull out test in two modes: the initial and deformed configurations. In the deformed shape, both contact and nonlinear spring elements are shown. It can be observed that the length of these elements increases by exerting a pullout force, which states the opening of the interface, as soon as a longitudinal load is exerted on the rod.

4. Evaluation of contact parameters

For the analysis of mechanical interaction between rod and concrete, some appropriate values for the contact element parameters Kn, Ks, μ , int (initial interference) should be evaluated. The procedure for evaluation of Kn, Kscan be made by assuming a predefined value for Kn, following a gradual increase in the value of Ks. For each corresponding pair of values of the parameters Kn and Ks, a separate analysis is made and the amount of final pull-out







Fig. 3 (a) slip and load versus ks diagrams- kn evaluation, (b) Slip and load versus kn diagrams- ks evaluation, (c) Slip versus ks diagrams- kn evaluation



Fig. 4 Bond strength versus slip diagrams: (a) μ =0.21 (b) μ =0.18

load along with the slip at the loaded end and final displacement of the reinforcement are derived. As can be seen in Fig. 3, for a specified point, any further increase in the value of Ks doesn't change the relative slip considerably. However, a small decremented change in the value of Ks results in merely high variation in the value of slips or end displacement. A high slope of the curve can be observed. This point is similar to "turned-point" in mathematics and called here as "critical point" (Fig. 3). Now a new iterative procedure is begun in which Ks is fixed at the amount derived from previous stage (the amount corresponding to critical point on the graph). As demonstrated in Fig. 3, by increasing Kn gradually, we can obtain a good approximation of Kn at the "critical point". A third procedure should be conducted similar to the first procedure. By increasing the value of Ks in an incremental manner, it is easily observed that the obtained value of Ks corresponding to the critical point is quite similar to that gained in the first procedure. This indicates that Ks equals to 5.0E7 and Kn equals to 8.0E8 are acceptable evaluations for the contact element parameters. The initial interference, which was derived from Al-Zahrani test (Bakis et al. 1998), was about (3.5-3.6) μ m. This value can be also concluded theoretically.

According to Al-Zahrani test (Bakis *et al.* 1998), a 40°C decrease in temperature of the whole system must result in 0.7 MPa reductions in total average bond strength (the ultimate load divided by the lateral surface of the part of rod within the bond length). It is clear that the bigger value of coefficient of friction applied in simulation results in greater ultimate load and average bond strength. Thus μ will be increased gradually in the model and its variation in the bond strength due to 40°C decrease of temperature can be



Fig. 5 Bond strength versus slip for contact parameters derived from calibration stage

measured.

The values of Ks and Kn, which have been applied in this analysis are exactly those derived from the iterative procedure explained above. The obtained coefficient of friction is 0.25. However, the proposed value from experiments is approximately between 0.18 and 0.2.

As mentioned in previous sections, for a fixed value of *Ks*, increasing the value of *Kn* relative to its corresponding amount at the critical point doesn't affect the response of system very much. Of course it is true for μ =1 so that the effect of coefficient of friction on the system response is neglected and the tangential force always lies on the linear branch of frictional behavior curve. So *Kn* is increased up to 2.0E9 and the expected reduction in bond strength is gained for a μ parameter equal to 0.21. This value is very near to the value observed in tests (0.18-0.2) and could be proposed as an appropriate evaluation.

5. Calibration of contact parameters

In order to calibrate the evaluated parameters, the loadslip curve has been applied as a suitable criterion. Al-Zahrani derived such a curve for an experimental sample of the model used in this research (Bakis et al. 1998). So parameters calculated from the previous stage (Ks=5.0E7, Kn=2.0E9, μ =0.21) were inserted into the model and a reanalysis was carried out. Fig. 4(a) describes a comparison between the curves obtained from the theory and experiment. Although the mechanical behavior is similar in both cases, a considerable difference between the resulted maximum pull-out loads in both cases can be observed. To gain a numerical response, which coincides with observations in reality in a better manner, the coefficient of friction is reduced to 0.18. It can be seen that the maximum pull-out loads in both theory and experiments are quite identical. (Fig. 4(b)

The best algorithm for a further decrease in the maximum tolerable pull-out load to make the uniform branch of graph as a good average approximation of the experimental data measured after the maximum load carried out is more reduction in the value of μ . So the analysis has been carried out one more time, applying the following parameters: *Ks*=5.0E7, *Kn*=2.0E9, μ =0.16 and the obtained load-slip curves for both ends of the rod for both experimental and numerical solutions are compared in Fig. 5.

It can be observed that the resulted curves in both cases are appropriately similar. Presence of an elasto-plastic behavior in the numerical analysis is because of using linear-full plastic material properties for transversely isotropic material of composite in various orthogonal directions due to computational and analytical limitations in the software applied for analysis. Also the mechanical behavior of concrete is assumed linear in modelling.

From Fig. 5, it is concluded that these parameters are appropriate evaluations for the analysis of the mechanical interaction of FRP reinforcement with concrete.

6. Conclusions

The purpose in the present paper was to propose a reliable finite element modelling of FRP smooth rods mechanical interaction with concrete by evaluation, calibration and validation of contact parameters. Friction is the main supplier of bond in smooth rods while mechanical interference (bearing) is the main cause of bond in lugged rods. Adding deformation increases bond strength and decreasing the deformation depth decreases the amount of bond strength. Modelling of smooth rods interaction with concrete should be done by applying contact elements. These elements are defined by these parameters: tangential stiffness (Ks), normal stiffness (Kn), coefficient of friction (μ) and initial interference (δ) . Also some nonlinear springs must be applied to simulate chemical adhesion. Process of proposing appropriate values for bond parameters Kn, Ks includes three stages: evaluation, calibration, validation. The suitable parameters resulted in this research for Ks is 5.0E7 and for Kn is 2.0E9. The suggested value for parameter μ from this research is 0.16. However, the proposed value from experiments is 0.18-0.20. Not all the parameters involved in reality can be considered in modelling. Also here the transversely isotropic material behavior can only be considered as linear-full plastic due to computational limitations so the numerical curves show a smoother and uniform behavior, although the experimental curves are very curved & crooked.

References

- Aghakhani, M., Suhatril, M., Mohammadhassani, M., Daie, M. and Toghroli, A. (2015), "A simple modification of homotopy perturbation method for the solution of Blasius equation in semi-infinite domains", *Math. Prob. Eng.*, **2015**, Article ID 671527, 7.
- Arabnejad Khanouki, M.M. et al. (2010), "Investigation of seismic behaviour of composite structures with concrete filled square steel tubular (CFSST) column by push-over and time-history analyses", Proceedings of the 4th International Conference on Steel & Composite Structures, Sydney, Australia, July.
- Khanouki, A., Mehdi, M., Ramli Sulong, N.H. and Shariati, M. (2011), "Behavior of through beam connections composed of CFSST columns and steel beams by finite element studying", *Adv. Mater. Res.*, **168**, 2329-2333.
- Ashour, A.F. and Kara, I.F. (2014), "Size effect on shear strength of FRP reinforced concrete beams", *Compos. Part B: Eng.*, 60, 612-620.

- Bakis, C.E., Uppuluri, V.S., Nanni, A. and Boothby, T.E. (1998), "Analysis of bonding mechanisms of smooth and lugged FRP rods embedded in concrete", *Compos. Sci. Technol.*, 58(8), 1307-1319.
- Bazzaz, M. (2018), "Experimental and analytical procedures to characterize mechanical properties of asphalt concrete materials for airfield pavement applications", Ph.D., University of Kansas.
- Bazzaz, M., Andalib, Z., Kheyroddin, A. and Kafi, M.A. (2015), "Numerical comparison of the seismic performance of steel rings in off-centre bracing system and diagonal bracing system", *Steel Compos. Struct.*, **19**(4), 917-937.
- Bazzaz, M., Darabi, M.K., Little, D.N. and Garg, N. (2018), "A straightforward procedure to characterize nonlinear viscoelastic response of asphalt concrete at high temperatures", *Transportation Research Record. Transportation Research Board 96th Annual Meeting*, 2672, 481-492.
- Benmokrane, B. and Tighiouart, B. (1996), "Bond strength and load distribution of composite GFRP reinforcing bars in concrete", *Mater. J.*, **93**(3), 254-259.
- Cosenza, E., Manfredi, G. and Realfonzo, R. (1997), "Behavior and modeling of bond of FRP rebars to concrete", *J. Compos. Constr.*, **1**(2), 40-51.
- Daie, M., Jalali, A., Suhatril, M., Shariati, M., Khanouki, M.A., Shariati, A. and Kazemi-Arbat, P. (2011), "A new finite element investigation on pre-bent steel strips as damper for vibration control", *Int. J. Phys. Sci.*, 6(36), 8044-8050.
- Feroldi, F. and Russo, S. (2016), "Structural behavior of all-FRP beam-column plate-bolted joints", *J. Compos. Constr.*, **20**(4), 04016004.
- Guo, J. and Cox, J.V. (2000), "An interface model for the mechanical interaction between FRP bars and concrete", *J. Reinf. Plast. Compos.*, **19**(1), 15-33.
- Hadi, M.N. (2007), "Behaviour of FRP strengthened concrete columns under eccentric compression loading", *Compos. Struct.*, 77(1), 92-96.
- Heydari, A. and Shariati, M. (2018), "Buckling analysis of tapered BDFGM nano-beam under variable axial compression resting on elastic medium", *Struct. Eng. Mech.*, **66**(6), 737-748.
- Hosseinpour, E., Baharom, S., Badaruzzaman, W.H.W., Shariati, M. and Jalali, A. (2018), "Direct shear behavior of concrete filled hollow steel tube shear connector for slim-floor steel beams", *Steel Compos. Struct.*, 26(4), 485-499.
- Ismail, M., Shariati, M., Awal, A., Chiong, C., Chahnasir, E., Porbar, A., ... and Khorami, M. (2018), "Strengthening of bolted shear joints in industrialized ferrocement construction", *Steel Compos. Struct.*, 28(6), 681-690.
- Jalal, M., Ramezanianpour, A.A., Pouladkhan, A.R. and Tedro, P. (2013), "Application of genetic programming (GP) and ANFIS for strength enhancement modeling of CFRP-retrofitted concrete cylinders", *Neur. Comput. Appl.*, 23(2), 455-470.
- Jalali, A., Daie, M., Nazhadan, S.V.M., Kazemi-Arbat, P. and Shariati, M. (2012), "Seismic performance of structures with pre-bent strips as a damper", *Int. J. Phys. Sci.*, 7(26), 4061-4072.
- Jerome, D.M. and Ross, C.A. (1997), "Simulation of the dynamic response of concrete beams externally reinforced with carbon-fiber reinforced plastic", *Comput. Struct.*, **64**(5), 1129-1153.
- Karimi, K., Tait, M.J. and El-Dakhakhni, W.W. (2011), "Testing and modeling of a novel FRP-encased steel–concrete composite column", *Compos. Struct.*, 93(5), 1463-1473.
- Khanouki, M.A., Sulong, N.R., Shariati, M. and Tahir, M.M. (2016), "Investigation of through beam connection to concrete filled circular steel tube (CFCST) column", *J. Constr. Steel Res.*, **121**, 144-162.
- Kheyroddin, A.B., Famili Fard, M. and Zahra, P.A. (2008a), "High performance and special concrete", *14th International*

Civil Engineering Student Conference, Semnan, Iran.

- Kheyroddin, A.E., Bazzaz, H. and Abed Pour, M. (2008b), "Evaluating the criteria of drift story in design with ETABS software", 14th International Civil Engineering Student Conference, Semnan, Iran.
- Khorami, M., Alvansazyazdi, M., Shariati, M., Zandi, Y., Jalali, A. and Tahir, M. (2017a), "Seismic performance evaluation of buckling restrained braced frames (BRBF) using incremental nonlinear dynamic analysis method (IDA)", *Earthq. Struct.*, 13(6), 531-538.
- Khorami, M., Khorami, M., Motahar, H., Alvansazyazdi, M., Shariati, M., Jalali, A. and Tahir, M.M. (2017b), "Evaluation of the seismic performance of special moment frames using incremental nonlinear dynamic analysis", *Struct. Eng. Mech.*, 63(2), 259-268
- Khorramian, K., Maleki, S., Shariati, M., Jalali, A. and Tahir, M. M. (2017), "Numerical analysis of tilted angle shear connectors in steel-concrete composite systems", *Steel Compos. Struct.*, 23(1), 67-85.
- Khorramian, K., Maleki, S., Shariati, M. and Sulong, N.R. (2015), "Behavior of tilted angle shear connectors", *PLoS ONE*, **10**(12), 1-11.
- Khorramian, K., Maleki, S., Shariati, M. and Sulong, R.N. (2016), "Behavior of tilted angle shear connectors (vol 10, e0144288, 2015)", *PLOS ONE*, **11**(2).
- Mansouri, I., Safa, M., Ibrahim, Z., Kisi, O., Tahir, M.M., Baharom, S. and Azimi, M. (2016), "Strength prediction of rotary brace damper using MLR and MARS", *Struct. Eng. Mech.*, 60(3), 471-488.
- Mansouri, I., Shariati, M., Safa, M., Ibrahim, Z., Tahir, M.M. and Petković, D. (2017), "Analysis of influential factors for predicting the shear strength of a V-shaped angle shear connector in composite beams using an adaptive neuro-fuzzy technique", *J. Intell. Manuf.*, 1-11.
- Bobaru, F., Mehrmashhadi, J., Chen, Z. and Niazi, S. (2018a), "Intraply fracture in fiber-reinforced composites: A peridynamic analysis", *Proceedings of the American Society for Composites-Thirty-Third Technical Conference*, 24-26.
- Mehrmashhadi, J., Tang, Y., Zhao, X., Xu, Z., Pan, J.J., Van Le, Q. and Bobaru, F. (2018b), "The effect of solder joint microstructure on the drop test failure: a peridynamic analysis", *IEEE Tran. Compon. Pack. Manuf. Technol.*, 9(1), 58-71.
- Mohammadhassani, M., Akib, S., Shariati, M., Suhatril, M. and Khanouki, M.A. (2014a), "An experimental study on the failure modes of high strength concrete beams with particular references to variation of the tensile reinforcement ratio", *Eng. Fail. Anal.*, **41**, 73-80.
- Mohammadhassani, M., Nezamabadi-Pour, H., Suhatril, M. and Shariati, M. (2013), "Identification of a suitable ANN architecture in predicting strain in tie section of concrete deep beams", *Struct. Eng. Mech.*, **46**(6), 853-868.
- Mohammadhassani, M., Nezamabadi-Pour, H., Suhatril, M. and Shariati, M. (2014b), "An evolutionary fuzzy modelling approach and comparison of different methods for shear strength prediction of high-strength concrete beams without stirrups", *Smart Struct. Syst.*, **14**(5), 785-809.
- Mohammadhassani, M., Suhatril, M., Shariati, M. and Ghanbari, F. (2014c), "Ductility and strength assessment of HSC beams with varying of tensile reinforcement ratios", *Struct. Eng. Mech.*, 48(6), 833-848.
- Mohebi, B., Hosseinifard, S.M. and Bastami, M. (2016), "Plastic hinge characteristics of RC rectangular columns with Fiber Reinforced Polymer (FRP)", Comput. Concrete, 18(4), 853-876.
- Moy, C.K. (2018), "Structural performance of a precast beam to column connection strengthened with FRP under monotonic loading", *Appl. Mech. Mater.*, 878, 121-125.

Emami, S., Choopan, Y. and Parsa, J. (2016), "Estimation of the

shear strength capacity of masonry walls improved with Fiber Reinforced Mortars (FRM) using ANN-GMDH approach", J. Concrete Struct. Mater., 1(2), 47-59.

- Naderpour, H., Kheyroddin, A., Amiri, G.G. and Vaez, S.H. (2011), "Estimating the behavior of FRP-strengthened RC structural members using artificial neural networks", *Procedia Eng.*, **14**, 3183-3190.
- Nasrollahi, S., Maleki, S., Shariati, M., Marto, A. and Khorami, M. (2018), "Investigation of pipe shear connectors using push out test", *Steel Compos. Struct.*, 27(5), 537-543.
- Nazerian, M. and Sadeghiipanah, V. (2013), "Cement-bonded particleboard with a mixture of wheat straw and poplar wood", *J. Forest. Res.*, 24(2), 381-390.
- Nosrati, A., Zandi, Y., Shariati, M., Khademi, K., Darvishnezhad Aliabad, M., Marto, A., Mu'azu, M.A., Ghanbari, E., Mahdizadeh, M.B., Shariati, A. and Khorami, M. (2018), "Structure of Portland cement and its major oxides and fineness", *Smart Struct. Syst.*, 22(4), 425-432.
- Paknahad, M., Bazzaz, M. and Khorami, M. (2018), "Shear capacity equation for channel shear connectors in steel-concrete composite beams", *Steel Compos. Struct.*, 28(4), 483-494.
- Rahimi, H. and Hutchinson, A. (2001), "Concrete beams strengthened with externally bonded FRP plates", J. Compos. Constr., 5(1), 44-56.
- Chahnasir, E.S., Zandi, Y., Shariati, M., Dehghani, E., Toghroli, A., Mohamed, E.T., ... and Khorami, M. (2018), "Application of support vector machine with firefly algorithm for investigation of the factors affecting the shear strength of angle shear connectors", *Smart Struct. Syst.*, 22(4), 413-424.
- Safa, M., Shariati, M., Ibrahim, Z., Toghroli, A., Baharom, S.B., Nor, N.M. and Petkovic, D. (2016), "Potential of adaptive neuro fuzzy inference system for evaluating the factors affecting steelconcrete composite beam's shear strength", *Steel Compos. Struct.*, 21(3), 679-688.
- Sakai, T., Kanakubo, T., Yonemaru, K. and Fukuyama, H. (1999), "Bond splitting behavior of continuous fiber reinforced concrete members", *Special Pub.*, **188**, 1131-1144.
- Sedghi, Y., Zandi, Y., Toghroli, A., Safa, M., Mohamad, E.T., Khorami, M. and Wakil, K. (2018), "Application of ANFIS technique on performance of C and L shaped angle shear connectors", *Smart Struct. Syst.*, 22(3), 335-340.
- Shahabi, S.E.M., Sulong, N.H., Shariati, M., Mohammadhassani, M. and Shah, S.N.R. (2016a), "Numerical analysis of channel connectors under fire and a comparison of performance with different types of shear connectors subjected to fire", *Steel Compos. Struct.*, 20(3), 651-669.
- Shahabi, S., Sulong, N., Shariati, M. and Shah, S. (2016b), "Performance of shear connectors at elevated temperatures-A review", *Steel Compos. Struct.*, 20(1), 185-203.
- Shariat, M., Shariati, M., Madadi, A. and Wakil, K. (2018), "Computational lagrangian multiplier method using optimization and sensitivity analysis of rectangular reinforced concrete beams", *Steel Compos. Struct.*, 29(2), 243-256.
- Shariati, A. (2014), "Behaviour of C-shaped angle shear connectors in high strength concrete", M.SC, Jabatan Kejuruteraan Awam, Fakulti Kejuruteraan, Universiti Malaya.
- Shariati, A., Sulong, N.R., Suhatril, M. and Shariati, M. (2012a), "Investigation of channel shear connectors for composite concrete and steel T-beam", *Int. J. Phys. Sci.*, 7(11), 1828-1831.
- Shariati, A., RamliSulong, N.H. and Shariati, M. (2012b), "Various types of shear connectors in composite structures: A review", *Int. J. Phys. Sci.*, 7(22), 2876-2890.
- Shariati, A., Shariati, M., Sulong, N.R., Suhatril, M., Khanouki, M.A. and Mahoutian, M. (2014a), "Experimental assessment of angle shear connectors under monotonic and fully reversed cyclic loading in high strength concrete", *Constr. Build. Mater.*, 52, 276-283.

- Shariati, M. (2013), "Behaviour of C-shaped shear connectors in steel concrete composite beams", PhD Thesis, Faculty of engineering University of Malaya, Kuala Lumpur, Malaysia.
- Shariati, M., Ramli Sulong, N., Suhatril, M., Shariati, A., Arabnejad Khanouki, M. and Sinaei, H. (2012c), "Fatigue energy dissipation and failure analysis of channel shear connector embedded in the lightweight aggregate concrete in composite bridge girders", *Fifth International Conference on Engineering Failure Analysis*, The Hague, The Netherlands, July.
- Shariati, M., Ramli Sulong, N.H., Maleki, S. and Arabnejad Kh, M.M. (2010), "Experimental and analytical study on channel shear connectors in light weight aggregate concrete", *Proceedings of the 4th International Conference on Steel & Composite Structures*, Sydney, Australia, July.
- Shariati, M., Sulong, N.R. and Khanouki, M.A. (2012d), "Experimental assessment of channel shear connectors under monotonic and fully reversed cyclic loading in high strength concrete", *Mater. Des.*, 34, 325-331.
- Shariati, M., Sulong, N.R., KH, M.A. and Mahoutian, M. (2011a), "Shear resistance of channel shear connectors in plain, reinforced and lightweight concrete", *Scientif. Res. Essay.*, 6(4), 977-983.
- Shariati, M., Ramli Sulong, N.H., Arabnejad Khanouki, M.M. and Shariati, A. (2011b), "Experimental and numerical investigations of channel shear connectors in high strength concrete", *Proceedings of the 2011 World Congress on Advances in Structural Engineering and Mechanics* (ASEM'11+), Seoul, South Korea.
- Shariati, M., Sulong, N.R., Shariati, A. and Khanouki, M.A. (2015), "Behavior of V-shaped angle shear connectors: experimental and parametric study", *Mater. Struct.*, 49(9), 3909-3926.
- Shariati, M., Sulong, N.R., Shariati, A. and Kueh, A.B.H. (2016), "Comparative performance of channel and angle shear connectors in high strength concrete composites: An experimental study", *Constr. Build. Mater.*, **120**, 382-392.
 Shariati, M., Ramli Sulong, N.H., Sinaei, H., Khanouki, A.,
- Shariati, M., Ramli Sulong, N.H., Sinaei, H., Khanouki, A., Mehdi, M. and Shafigh, P. (2011c), "Behavior of channel shear connectors in normal and light weight aggregate concrete (experimental and analytical study)", *Adv. Mater. Res.*, 168, 2303-2307.
- Shariati, M., Sulong, N.R., Suhatril, M., Shariati, A., Khanouki, M.A. and Sinaei, H. (2013), "Comparison of behaviour between channel and angle shear connectors under monotonic and fully reversed cyclic loading", *Constr. Build. Mater.*, **38**, 582-593.
- Shariati, M., Sulong, N.R., Suhatril, M., Shariati, A., Khanouki, M.A. and Sinaei, H. (2012e), "Behaviour of C-shaped angle shear connectors under monotonic and fully reversed cyclic loading: An experimental study", *Mater. Des.*, 41, 67-73.
- Shariati, M., Shariati, A., Sulong, N.R., Suhatril, M. and Khanouki, M.A. (2014b), "Fatigue energy dissipation and failure analysis of angle shear connectors embedded in high strength concrete", *Eng. Fail. Anal.*, **41**, 124-134.
- Shariati, M., Tahir, M.M., Wee, T.C., Shah, S.N.R., Jalali, A., Abdullahi, M.A.M. and Khorami, M. (2018), "Experimental investigations on monotonic and cyclic behavior of steel pallet rack connections", *Eng. Fail. Anal.*, 85, 149-166.
- Shariati, M. et al. (2017), "Assessment of stiffened angle shear connector under monotonic and fully reversed cyclic loading", *Fifth International Conference on Advances in Civil, Structural* and Mechanical Engineering - CSM 2017, Zurich, Switzerland.
- Sinaei, H., Jumaat, M.Z. and Shariati, M. (2011), "Numerical investigation on exterior reinforced concrete Beam-Column joint strengthened by composite fiber reinforced polymer (CFRP)", *Int. J. Phys. Sci.*, 6(28), 6572-6579.
- Sinaei, H., Shariati, M., Abna, A.H., Aghaei, M. and Shariati, A.

(2012), "Evaluation of reinforced concrete beam behaviour using finite element analysis by ABAQUS", *Scientif. Res. Essay.*, **7**(21), 2002-2009.

- Tahmasbi, F., Maleki, S., Shariati, M., Sulong, N.R. and Tahir, M.M. (2016), "Shear capacity of C-shaped and L-shaped angle shear connectors", *PloS one*, **11**(8), e0156989.
- Toghroli, A., Darvishmoghaddam, E., Zandi, Y., Parvan, M., Safa, M., Abdullahi, M.A.M., ... and Khorami, M. (2018a), "Evaluation of the parameters affecting the Schmidt rebound hammer reading using ANFIS method", *Comput. Concrete*, 21(5), 525-530.
- Toghroli, A., Shariati, M., Sajedi, F., Ibrahim, Z., Koting, S., Mohamad, E.T. and Khorami, M. (2018b), "A review on pavement porous concrete using recycled waste materials", *Smart Struct. Syst.*, 22(4), 433-440.
- Toghroli, A., Suhatril, M., Ibrahim, Z., Safa, M., Shariati, M. and Shamshirband, S. (2016), "Potential of soft computing approach for evaluating the factors affecting the capacity of steel– concrete composite beam", J. Intell. Manuf., 29(8), 1793-1801.
- Toghroli, A., Mohammadhassani, M., Suhatril, M., Shariati, M. and Ibrahim, Z. (2014), "Prediction of shear capacity of channel shear connectors using the ANFIS model", *Steel Compos. Struct.*, **17**(5), 623-639.
- Triantafillou, T.C. and Plevris, N. (1992), "Strengthening of RC beams with epoxy-bonded fibre-composite materials", *Mater. Struct.*, 25(4), 201-211.
- Wei, X., Shariati, M., Zandi, Y., Pei, S., Jin, Z., Gharachurlu, S., ... and Khorami, M. (2018), "Distribution of shear force in perforated shear connectors", *Steel Compos. Struct.*, 27(3), 389-399.
- Yang, K.H., Byun, H.Y. and Ashour, A.F. (2009), "Shear strengthening of continuous reinforced concrete T-beams using wire rope units", *Eng. Struct.*, **31**(5), 1154-1165.
- Zhao, J., Chen, Z., Mehrmashhadi, J. and Bobaru, F. (2018), "Construction of a peridynamic model for transient advectiondiffusion problems", *Int. J. Heat Mass Transf.*, **126**, 1253-1266.

CC